

Natural Berber Twist

Technical Specification

	CONSTRUCTION MACHINE GAUGE PILE HEIGHT TUFT DENSITY PILE WEIGHT	ISO 1766	ELITE 1/8th Gauge 7.5 mm 120,900 tufts/m ² 1,525 gms/m ² 45 oz/yd ²	DELUXE 1/8th Gauge 9.1 mm 127,100 tufts/m ² 1,864 gms/m ² 55 oz/yd ²
	TOTAL CARPET WEIGHT CARPET THICKNESS WIDTH	ISO 8543	2,463 gms/m ² 10.6 mm 4 & 5 metre	2,802 gms/m ² 12.3 mm 4 & 5 metre
	COMPOSITION PILE CONTENT PRIMARY BACKING SECONDARY BACKING	ISO 1833	80% Wool, 10% Nylon, 10% Tuftbond Woven Polypropylene Woven Secondary	80% Wool, 10% Nylon, 10% Tuftbond Woven Polypropylene Woven Secondary
	PERFORMANCE SUITABILITY WIRA ABRASION TEST	PD 6527:Clause 17	Extra Heavy Domestic Exceeds 23,100 Rubs	Extra Heavy Domestic / Medium Contract Exceeds 25,300 Rubs
	STATIC LOADING	ISO 3416	22.1% Thickness Loss after 24 hrs recovery	19.5% Thickness Loss after 24 hrs recovery
	DYNAMIC LOADING	ISO 2094	30.6% Thickness Loss after 1,000 impacts	29.5% Thickness Loss after 1,000 impacts
	TUFT ANCHORAGE	ISO 4919	Above 1kg	Above 1kg
	COLOUR FASTNESS LIGHT FASTNESS WET FASTNESS SHAMPOO FASTNESS	ISO 105-B02 ISO 105-E01 ISO 18168	5 on all colours 4 on all colours 4/5 on all colours	5 on all colours 4/5 on all colours 4/5 on all colours
	THERMAL VALUE TOG VALUE THERMAL RESISTANCE	ISO 5085-1	1.66 Tog 0.16 m ² k/w	2.0 Tog 0.2 m ² k/w
	FLAMMABILITY CE MARK RATING HOT METAL NUT TEST METHENAMINE PILL TEST	CE BS4790 ISO 6925	Dfl, S1 Pass - Low radius of ignition Pass	Dfl, S1 Pass - Low radius of ignition Pass
	CHEMICAL IMPACT FORMALDEHYDE	CE	E1	E1
	BIOLOGICAL ATTACK MOTH / INSECT RESISTANT		Eulan Treated	Eulan Treated
	ANTI STATIC		-0.2 kv (Requirement less than +2.0kv)	-0.4 kv (Requirement less than +2.0kv)

General Information

INSTALLATION - In all contract locations an 'all-over' stick down method is recommended to BS 5325 (1983). If underlay is required it should be of a firm and unyielding type and where installed in larger contract areas the carpet should be power stretched. For quantity orders requiring colour matching, please state at time of ordering.

MAINTENANCE - To maintain your carpet's appearance it is recommended that it is vacuumed at least three times per week, to remove particles of dirt and dust. An upright vacuum with beater bar and brush is recommended for use with cut pile carpets. Please note, over time, regular foot traffic will flatten the pile surface in the main walkways, causing areas of differential wear.

These areas will appear lighter or shaded in comparison to the less frequently used parts. This shading / tracking or flattening happens to all carpets with a pile surface and as such is not accepted as the basis for any complaint. Similarly Pile Reversal (or watermarking) is a phenomenon that can affect all cut pile carpets and as such is not accepted as a manufacturing fault.

MATCHING - This sample may not be from the same production batch as current stock and therefore should be used as a guide and not as an exact match. Equally matching between 5 metre and 4 metre widths cannot be guaranteed.

IMPORTANT - Minimum order length is 1.5 metres.