

Trinity

Technical Specification

	CONSTRUCTION MACHINE GAUGE PILE HEIGHT TUFT DENSITY PILE WEIGHT	ISO 1766 ISO 1763	1/8th Gauge 10.7 mm 133,299 tufts/m ² 1,797 gms/m ² 53 oz/yd ²
	TOTAL CARPET WEIGHT CARPET THICKNESS WIDTH	ISO 8543 ISO 1765	2,733 gms/m ² 13.5 mm 4 & 5 metre
	COMPOSITION PILE CONTENT PRIMARY BACKING SECONDARY BACKING	ISO 1833	100% Excelon Polypropylene Woven Polypropylene Woven Secondary
	PERFORMANCE SUITABILITY WIRA ABRASION TEST STATIC LOADING DYNAMIC LOADING TUFT ANCHORAGE	ISO 10361 PD 6527:Clause 17 ISO 3416 ISO 2094 ISO 4919	Extra Heavy Domestic/Medium Contract Exceeds 26,100 Rubs 17.9% Thickness Loss after 24 hrs recovery 35.6% Thickness Loss after 1,000 impacts Above 0.75kg
	COLOUR FASTNESS LIGHT FASTNESS WET FASTNESS SHAMPOO FASTNESS	ISO 105-B02 ISO 105-E01 ISO 18168	6 on all colours 5 on all colours 5 on all colours
	THERMAL VALUE TOG VALUE THERMAL RESISTANCE	ISO 5085-1	1.6 Tog 0.16m ² k/w
	FLAMMABILITY CE MARK RATING HOT METAL NUT TEST METHENAMINE PILL TEST	CE BS 4790 ISO 6925	Efl High Radius of Ignition Pass
	CHEMICAL IMPACT FORMALDEHYDE	CE	E1
	BIOLOGICAL ATTACK MOTH / INSECT RESISTANT		Insect & rot proof
	ANTI STATIC		-0.3kv (Requirement less than +2.0kv)

General Information

INSTALLATION - In all contract locations an 'all-over' stick down method is recommended to BS 5325 (1983). If underlay is required it should be of a firm and unyielding type and where installed in larger contract areas the carpet should be power stretched. For quantity orders requiring colour matching, please state at time of ordering.

MAINTENANCE - To maintain your carpet's appearance it is recommended that it is vacuumed at least three times per week, to remove particles of dirt and dust. An upright vacuum with beater bar and brush is recommended for use with cut pile carpets. Please note, over time, regular foot traffic will flatten the pile surface in the main walkways, causing areas of differential wear.

These areas will appear lighter or shaded in comparison to the less frequently used parts. This shading / tracking or flattening happens to all carpets with a pile surface and as such is not accepted as the basis for any complaint. Similarly Pile Reversal (or watermarking) is a phenomenon that can affect all cut pile carpets and as such is not accepted as a manufacturing fault.

MATCHING - This sample may not be from the same production batch as current stock and therefore should be used as a guide and not as an exact match. Equally matching between 5 metre and 4 metre widths cannot be guaranteed.

IMPORTANT - Minimum order length is 1.5 metres.

Greenwood & Cope Ltd

Brookhouse Mill, Greenmount, Bury, Greater Manchester, BL8 4HR
T: 01204 881234 | F: 01204 887722 | info@cormarcarpets.co.uk

www.cormarcarpets.co.uk

December 2022